



POWDER COATING

Technical Data Sheet

Highlights

PPG’s Primeron powder coatings are durable primers with exceptional corrosion protection for a variety of market segments.

PPG’s “World Class” Primer Powder Coatings provide a combination of good physical and chemical resistance properties. This specialized line of zinc-rich epoxy, epoxy, and epoxy-polyester primers are manufactured to meet the increasing requirement demands of the automotive and industrial markets. These sophisticated products are the solution to your corrosion, durability, and physical property requirements. An unsurpassed application development program enables consistently friendly use on a variety of substrates.

- Available in a wide range of colors and glosses
- For interior use only
- Good chemical resistance



PRODUCT APPROVALS

Specifically formulated to meet the requirements of AAMA 2604 when applied over correctly cleaned substrate and appropriate AAMA topcoat used.

PRODUCT CHARACTERISTICS

Formulated for excellent outgassing (OGF) properties

TEST CONDITIONS

Property	Test method	Value
Substrate		Pretreated aluminum panels
Recommended Thickness	ASTM D 7091	2.0 - 3.0 mils
Curing Conditions	Metal Temperature	8 min @ 350 °F

PRODUCT PROPERTIES

Property	Test method	Value
Appearance	Visual Inspection	Smooth
Gloss 60°	ASTM D 523	75 - 85
Adhesion	ASTM D 3359	100% (5B Pass)
Hardness	ASTM D 3363	2H Pencil (Eagle)
Impact - Direct	ASTM D 2794	100 in-lbs
Impact - Reverse	ASTM D 2794	100 in-lbs
Conical Mandrel	ASTM D 522	1/8" Mandrel
Salt spray	ASTM B 117	3000 hrs Blister rating - 8 minimum Scribe rating - 7 minimum
Humidity	ASTM D 1735	3000 hrs Blister rating - 8 minimum
Specific gravity	Calculated	1.58 ± .05
Theoretical coverage	Calculated	122 ft²/lbs at 1.0 mil 24.9 m²/kg at 25 µm



POWDER COATING

Technical Data Sheet

CURING WINDOW* (object temperature)

See Cure Curve PCM-003

20 min @ 275 °F (135 °C)
10 min @ 300 °F (149 °C)
5 min @ 350 °F (177 °C)

*Temperature and time to be adjusted to accomplish proper curing of coating. This can be achieved using infrared, convection, or combination ovens.

STORAGE STABILITY

12 months at 80 °F maximum

Materials need to be stored in sealed plastic bags under dry and cool conditions. Do not expose to sunlight.

PPG recommends that all material be used in FIFO order (first in - first out). Materials that exceed the recommended shelf life should be tested prior to use.

SUBSTRATE PREPARATION

Surface preparation should be chosen according to the type of substrate and required performance.
The coater should test the suitability of the surface preparation before the application using appropriate test methods.

APPLICATION RECOMMENDATIONS

Electrostatic Spray
Coating can be applied with automatic and manual devices.
Substrate should be correctly cleaned before use.
Do not mix this product with other powder coatings.
Color and finish influenced by film thickness: a good control of the film thickness will help the consistency of the aspect.

HEALTH AND SAFETY

For comprehensive Health, Safety, and Environmental advice, please refer to the relevant Safety Data Sheets, and information printed on the product label.

* Statements and methods described herein are based upon the best information and practices known to PPG Industries, Inc. ("PPG"). Any statements or methods mentioned herein are general suggestions only and are not to be construed as representations or warranties as to safety, performance, or results. Since the suitability and performance of the product is highly dependent on the product user's processes, operations, and numerous other user-determined conditions, the user is solely responsible for, and assumes all responsibility, risk and liability arising from, the determination of whether the product is suitable for the user's purposes, including without limitation substrate, application process, pasteurization and/or processing, and end use. No testing, suggestions or data offered by PPG to the user shall relieve the user of this responsibility. PPG does not warrant freedom from patent infringement in the use of any formula or process set forth herein. Continuous improvements in coatings technology may cause future technical data to vary from what is in this bulletin. Contact your PPG representative for the most up to date information.

www.ppg.com & www.ppgindustrialcoatings.com & powder@ppg.com