



ENVIROCRON® Powder Coat

Polyester TGIC Ultra Durable
PCTB79195 - FED STD 595 16515

POWDER COATING

Technical Data Sheet

Highlights

PPG’s Enviracryl™ and Envirocron™ powder coatings are aesthetically pleasing, produce a durable uniform finish and can be custom formulated with finishes from high gloss to low gloss, and in a variety of textures.

PPG’s “World Class” Ultradurable Polyester Powder Coatings provide a combination of good physical and chemical resistance properties with excellent resistance to outdoor weathering. This extensive line of Polyester Powders is manufactured to meet the increasing requirement demands of the appliance and industrial markets. These sophisticated Polyesters are the solution to your smoothness, low-bake, durability and physical property requirements. An unsurpassed application development program enables consistently friendly use on a variety of substrates.

- Available in a wide range of colors and glosses
- Good chemical resistance

TEST CONDITIONS

Property	Test method	Value
Substrate		Pretreated steel panels
Recommended Thickness	ASTM D 7091	2.0 - 3.0 mils
Curing Conditions	Metal Temperature	15 min @ 375 °F

PRODUCT PROPERTIES

Property	Test method	Value
Appearance	Visual Inspection	Smooth
Gloss 60°	ASTM D 523	80 Minimum
Adhesion	ASTM D 3359	100% (5B Pass)
Hardness	ASTM D 3363	2H Pencil (Eagle)
Impact - Direct	ASTM D 2794	160 in-lbs
Impact - Reverse	ASTM D 2794	160 in-lbs
Conical Mandrel	ASTM D 522	1/8" Mandrel
Specific gravity	Calculated	1.59 ± .05
Theoretical coverage	Calculated	121 ft²/lbs at 1.0 mil 24.8 m²/kg at 25 µm





POWDER COATING

Technical Data Sheet

STORAGE STABILITY

24 months at 80 °F maximum

Materials need to be stored in sealed plastic bags under dry and cool conditions. Do not expose to sunlight.

PPG recommends that all material be used in FIFO order (first in - first out). Materials that exceed the recommended shelf life should be tested prior to use.

SUBSTRATE PREPARATION

Surface preparation should be chosen according to the type of substrate and required performance.

The coater should test the suitability of the surface preparation before the application using appropriate test methods.

APPLICATION RECOMMENDATIONS

Electrostatic Spray

Coating can be applied with automatic and manual devices.

Substrate should be correctly cleaned before use.

Do not mix this product with other powder coatings.

Color and finish influenced by film thickness: a good control of the film thickness will help the consistency of the aspect.

HEALTH AND SAFETY

For comprehensive Health, Safety, and Environmental advice, please refer to the relevant Safety Data Sheets, and information printed on the product label.

* Statements and methods described herein are based upon the best information and practices known to PPG Industries, Inc. ("PPG"). Any statements or methods mentioned herein are general suggestions only and are not to be construed as representations or warranties as to safety, performance, or results. Since the suitability and performance of the product is highly dependent on the product user's processes, operations, and numerous other user-determined conditions, the user is solely responsible for, and assumes all responsibility, risk and liability arising from, the determination of whether the product is suitable for the user's purposes, including without limitation substrate, application process, pasteurization and/or processing, and end use. No testing, suggestions or data offered by PPG to the user shall relieve the user of this responsibility. PPG does not warrant freedom from patent infringement in the use of any formula or process set forth herein. Continuous improvements in coatings technology may cause future technical data to vary from what is in this bulletin. Contact your PPG representative for the most up to date information.

www.ppg.com & www.ppgindustrialcoatings.com & powder@ppg.com